


Biomaterials and Cell- Biomaterial Interactions

Module 3, Lecture 2

20.109 Spring 2010

Lecture 1 review

- What is tissue engineering?
- Why is tissue engineering?
- Why care about cartilage?
- What are we asking in Module 3?




Topics for Lecture 2

- Introduction to biomaterials
 - properties
 - examples
- Cartilage composition
 - collagen
 - proteoglycans

Module 3 goals

- Lab concepts/techniques
 - Mammalian cell culture
 - Phenotypic assays
- Short informal report
 - Accountability to 20.109 community
- Discussions in lecture
 - Engage with meta-scientific issues, ethics, etc.
- Research idea presentation
 - Investigate literature independently
 - Exercise scientific creativity
 - Design experiments to address a specific question

Today in Lab: M3D2



0.5 mL beads,
6 mL media

0.5 mL beads,
6 mL media

1 condition per plate (2 plates total).




2 wells per plate (split 1 mL of beads).

1 well for viability test, 1 for collagen tests.

Properties of biomaterials



- Physical/mechanical

- strength
- elasticity
- architecture (e.g., pore size)




- Chemical

- degradability
- water content
- toxicity



- Biological

- motifs that cells recognize
- release of biological components



- Lifetime

The right material for the job

- Metals
 - Ti, Co, Mg alloys
 - pros: mechanically robust
 - applications: orthopedics, dentistry
- Ceramics
 - Al_2O_3 , Ca-phosphates, sulfates
 - pros: strength, bonding to bone
 - applications: orthopedics, dentistry
- Polymers
 - diverse, tunable properties
 - applications: soft tissues


General: B. Ratner, ed. *Biomaterials Science*, 1996.

Image: Porter et al., *Biomaterials* **25**:3303 (2004).

Metal hip
implant



<http://www.weisshospital.com/joint-university/hip/metal.html>



Si-HA


Bone

Polymers are diverse and tunable

- Linear polymers
 - repeated chemical unit
- Co-polymers
 - heterogeneous repeats
- With increasing MW get
 - increased entanglements
 - increased strength
 - decreased processability
- Varying properties
 - hydrophilicity
 - gas permeability
 - stability
 - ease of chemical modification
 - mechanical properties




Poly(ethylene glycol)



Poly(lactic-co-glycolic acid)

[public domain image]

Free radical polymerization



- Network structure
 - covalently cross-linked chains
 - water-swollen (if hydrophilic)

Properties of hydrogels

- Mimic soft tissues
 - water content
 - elasticity
 - diffusivity
- Synthesis at physiological conditions
 - temperature
 - pH
 - UV light: spatio-temporal control; safe
- Injectability
- Chemical modification



(Stachowiak & Irvine)


Review: Nguyen KT & West JL, *Biomaterials* **23**:4307 (2002)

Materials must be biocompatible


- Avoid **bio-incompatibility**
 - immunogenicity
 - bacterial adhesion
 - clot formation
 - toxicity
- Material properties
 - sterility
 - resistance to protein adhesion
 - material *and* its degradation products non-toxic

Data from: Zavan B, et al.,
FASEB J **22**:2853 (2008).

Normal artery




Occluded artery




Beyond bioinert: bioactive materials

- Attach proteins/peptides for
 - adhesion
 - degradability
- Release cytokines for
 - proliferation
 - differentiation
 - attraction

Fibroblasts on polymer-peptide gels (Stachowiak).



- e.g., West JL and Hubbell JA *Macromolecules* **32**:241 (1999)




Interlude: what (if any) should be off-limits to science?

1. “Hallucinogens have doctors tuning in again”
NY Times April 2010

Researchers from around the world are gathering this week in San Jose, Calif., for the largest conference on psychedelic science held in the United States in four decades. They plan to discuss studies of psilocybin and other psychedelics for treating depression in cancer patients, obsessive-compulsive disorder, end-of-life anxiety, post-traumatic stress disorder and addiction to drugs or alcohol.

2. “Towards responsible use of cognitive-enhancing drugs by the healthy” *Nature* **456**, 702-705


TE constructs to study cell migration




Gobin AS & West J, *J Biomed Mater Res* 67:255 (2003)

Natural vs. synthetic polymers

- Natural pros/cons
 - built-in bioactivity
 - poor mechanical strength
 - immunogenicity (xenologous sources)
 - lot-to-lot variation, unpredictable
- Synthetic pros/cons
 - predicting biocompatibility is tough
 - mechanical and chemical properties readily altered
 - minimal lot-to-lot variation
- Synthetic advantages: tunable and reproducible




Revisiting cartilage structure



Water-swollen, heterogeneous, avascular tissue.

Structure of collagen(s)

- 1° structure:
 - Gly-X-Y repeats
 - proline, hydroxyproline
- 3° structure: triple helix
 - Gly: flexibility
 - Hyp: H-bonding
- 4° structure: fibrils
 - many but not all collagens
 - cross-links via lysine, hydroxylysine
 - periodic banding observable




Molecular image made using *Protein Explorer* (PDB ID: 1bkv).
Fibril image from public domain.

E. Vuorio & B. de Crombrughe *Annu Rev Biochem* 59:837 (1990)

Collagen composition in cartilage

- Collagen types vary in
 - location
 - glycosylation
 - higher-order structure
 - homo- (II) or hetero- (I) trimers
- Cartilage collagens
 - Type II with IX and XI
 - exact roles of IX and XI unknown
 - inter-fibrillar cross-links
 - modulate fibril diameter
 - mutations to IX, XI, II cause disease
 - others(III, VI, X, XII, XIV)
- **Little collagen turnover in adult cartilage**




D.J. Prockop *Annu Rev Biochemritis Res* 64:403 (1995)

D. Eyre (2002)

D. Eyre *Arthritis Res* 4:30 (2002)

Proteoglycans are bulky and charged


- Proteins with GAG side chains
 - GAG is glycosaminoglycan
 - many charged groups: COO^- , SO_3^-
- Main cartilage PG is aggrecan
 - GAG is primarily chondroitin sulfate (CS)
 - aggrecans polymerize via hyaluronin (HA)



Chondroitin sulfate
(public domain image)

Aggrecan monomer

R.V. Iozzo *Annu
Rev Biochem*
67:609 (1998)




PG form heterogeneous aggregates

- Monomer > 1M, aggregates > 100M Da
- Average size decreases
 - with age
 - with osteoarthritis
- Aggrecenase inhibitors may be a target
- Under compression: water exuded, osmotic resistance


Aggrecan aggregate

C.B & W. Knudson
Cell & Dev Bio
12:69 (2001)



Cartilage structure and function


- Cartilage composition
 - dry weight: CN 50-75% ; PG 15-30%
 - water: 60-80%
 - cells: 5-10% by volume
- Requirements of a joint
 - load transfer (bone/bone, bone/muscle)
 - flexibility, lubrication
- Role of PG
 - high compressive strength (osmotic swelling)
 - low permeability, friction coefficient reduces wear and tear
- Role of CN
 - high tensile strength (~GPa)
 - contain swelling forces of PG



V.C. Mow, A. Ratcliffe, and S.LY. Woo, eds. *Biomechanics of Diarthrodial Joints* (Vol. I) Springer-Verlag New York Inc. 1990

Lecture 2: conclusions

- A variety of biomaterials are used in TE.
- Cell-material interactions can be (+), (-), or neutral.
- Hydrogels are useful for soft tissue engineering: they mimic such tissue and are easy to modify.
- The composition of cartilage supports its functions.



Next time... intro to statistics, and to standards in scientific communities.